

# WB 707

## Underbody Rust proofing

### Introduction

---

Sierra water based or Non Regulated WB 707 Underbody Black rust proofing is an extremely hardwearing bitumous style of coating that provides high adhesion and resistance to abrasion. May be applied to most surfaces, including; bare and painted steel, alloys including brass, and most styles of paint. May also be used over other non bitumous rustproofings commonly found in wheel arches of four wheel drives in Australia.

### Typical Properties

---

Not for  
Specification  
purposes

Properties	Sierra Clear Skin
Appearance	Viscous black liquid
Drying Time (minimum)	65 mins @ 20°
Recoating Time (minimum)	3 hours @ 20°
Serviceable within	24 to 48 hours depending upon film thickness.
Approximate Coverage	11 sq meters per litre
Thinning	Water in hot dry conditions – to 5%
Cleaning up	Warm Water (may use 'Rinse Eaze')
VOC	24 grams per litre

### Preparation and Application

---

Ensure the areas to be coated are clean, dry and free from dust, dirt and grease. If oil is present, first degrease with Citrus 6000 and let dry thoroughly before application to ensure maximum adhesion.

Application is best done using air or airless application, however brush may be used if necessary in some parts.

Maintain adequate ventilation throughout the drying and curing phase to ensure the WB 707 is properly and evenly cured. Poor ventilation may inhibit curing and performance.

Every endeavor has been made to ensure that the information contained in this publication is reliable and offered in good faith. It is meant to describe the safety requirements of our products and should not be construed as guaranteeing specific properties. Customers are encouraged to conduct their own tests as end user suitability of the product for particular uses is beyond our control. The information is not intended as an inducement to bargain and no warranty expressed or implied is made as to its accuracy, reliability or completeness. Sierra (Aust) Pty Ltd accepts no liability for loss, injury or damage arising from reliance upon the information contained in this data sheet except in conjunction with the proper use of the product to which it refers. Due care should be taken that the use and disposal of this product is in compliance with appropriate Federal, State and Local Government regulations.